

COMPEX™ R200
Release Film

Ideally suited to debulking applications.

FEATURES & BENEFITS

- Exhibits excellent release characteristics from all commonly used resin systems.
- Ideal for use in resin infusion applications.
- Available perforated or non-perforated.
- Cost optimized release film suitable for use in a wide range of composite processing.
- High elongation and excellent conformability.
- Colored red for ease of identification.
- Available perforated or non-perforated.

PROPERTIES

Maximum use temperature	150°C / 302°F
Color	Red
Film	Blended polymer
Standard perforation patterns	Contact us for full details
Tensile strength (at break)	35MPa / 5076psi
Elongation (at break)	500%
Density	0.9g/cm ³ / 0.52oz/in ³

AVAILABILITY

Thicknesses	30 and 50µm	0.001 and 0.002in
Standard width	Up to 1.52m	Up to 1.66yd
Standard length	400m	437yd

STORAGE

Store in original packaging.

HEALTH & SAFETY

Please refer to the product MSDS for safe handling, personal protective equipment recommendations and disposal considerations.

CONTACT US:

Stockholmer Platz 1, 70173, Stuttgart, Germany
+49 711 87089000
info@apspolymer.de
www.apspolymer.de

For UK:

www.apspolymer.co.uk
sales@apspolymer.co.uk