

Ideally suited to aerospace applications.

FEATURES & BENEFITS

- High temperature release film, mainly used during the processing of flat or simple curvature components.
- Offers a low cost alternative to other high temperature aerospace qualified release films.
- Exhibits excellent release characteristics from all commonly used resin systems.
- Colored red for ease of identification on the cured laminate.

PROPERTIES

Maximum use temperature	204°C / 400°F
Color	Red
Film	PMP
Standard perforation patterns	Contact us for full details
Tensile strength (at break)	30MPa / 4351psi
Elongation (at break)	285%
Density	0.835g/cm ³ / 0.48oz/in ³

AVAILABILITY

Thicknesses	Up to 50µm	0.002in
Standard width	1.1m, 1.37m	1.2yd, 1.5yd
Standard length	400m	437yd
Internal core size	76mm	3in

STORAGE

Store in original packaging.

HEALTH & SAFETY

Please refer to the product MSDS for safe handling, personal protective equipment recommendations and disposal considerations.

CONTACT US:

Stockholmer Platz 1, 70173, Stuttgart, Germany
+49 711 87089000
info@apspolymer.de
www.apspolymer.de

For UK:

www.apspolymer.co.uk
sales@apspolymer.co.uk